

# **EUWAX<sup>®</sup> G60**

|                       |                                                                                                                                                                                                                                          |                            |
|-----------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------|
| <b>Description</b>    | Solid, neutral dicarboxylic acid ester of saturated fatty alcohols                                                                                                                                                                       |                            |
| <b>Appearance</b>     | White powder, good free-flowing, odourless                                                                                                                                                                                               |                            |
| <b>Technical Data</b> | Drop point                                                                                                                                                                                                                               | 46~50℃                     |
|                       | Acid value                                                                                                                                                                                                                               | <2.0mg KOH/g               |
|                       | Iodine value                                                                                                                                                                                                                             | <1.0 gI <sub>2</sub> /100g |
|                       | Hydroxyl value                                                                                                                                                                                                                           | 0~10 mg KOH/g              |
|                       | Saponification value                                                                                                                                                                                                                     | 165~180mg KOH/g            |
| <b>Applications</b>   | For PVC                                                                                                                                                                                                                                  |                            |
|                       | ●rigid PVC processing                                                                                                                                                                                                                    |                            |
|                       | ●internal lubricant                                                                                                                                                                                                                      |                            |
|                       | ● highly compatible all-around lubricant                                                                                                                                                                                                 |                            |
| <b>Properties</b>     | For PVC                                                                                                                                                                                                                                  |                            |
|                       | ●as almost no influence on the plastification time                                                                                                                                                                                       |                            |
|                       | ●for adjusting the flow when working with complicated sections                                                                                                                                                                           |                            |
|                       | and injection mouldings                                                                                                                                                                                                                  |                            |
| <b>Dosage</b>         | 0.2 ~ 3.0phr                                                                                                                                                                                                                             |                            |
| <b>Net weight</b>     | 25kg/bag                                                                                                                                                                                                                                 |                            |
| <b>Storage</b>        | It is recommended to store EUWAX <sup>®</sup> G60 at room temperature and to protect the product against the effects of heat and frost.If stored in sealed original containers, EUWAX <sup>®</sup> G60 will keep for at least 24 months. |                            |